

IN THE CLAIMS

1. (Currently Amended) . A thermally insulated container (101) for the transport of cargo (102), said container (101) comprising panels (103) comprising at least one outer layer/wall (104) and at least one inner layer/wall (105), between which layers/walls foam material (106) is arranged between the layers/walls (104, 105), being of metal and having a thickness in excess of 50 μm , characterised in that the foam material is an essentially closed cell foam material, said cells (107) enclosing at least two gases (108), said gases (108) having a value λ for thermal conductivity which is lower than that of atmospheric air; and that the gases comprise at least one blowing-agent gas and at least one additive gas and are present in the cells in ~~an amount~~ a ratio by weight of blowing agent to additive ~~corresponding to a closed interval corresponding to the~~ ratio of 50:1 to 400:1.
2. (Original) A thermally insulated container according to claim 1, characterised in that the foam material (106) is a polyurethane foam.
3. (Previously Presented) A thermally insulated container according to claim 1, characterised in that the value for thermal conductivity is, at least for the additive gas, less than 20 mW/m^{°K}.
4. (Previously Presented) A thermally insulated container according to claim 1, characterised in that the additive gas comprises an inert gas, eg argon.
5. (Previously Presented) A thermally insulated container according to claim 1, characterised in that the layers/walls (104, 105) are manufactured from a steel alloy and/or an aluminium alloy.
6. (Previously Presented) A thermally insulated container according to claim 1, characterised in that the distance between the inner layer (105) and the outer layer (104) is at least 35 mm; and that the cavity between the plane parallel inner and outer layers/walls is filled with foam material, said material being in contact with both layers/walls and faces facing towards the foam material (106) and in the entire expanse thereof.

7. (Previously Presented) A thermally insulated container according to claim 1, characterised in that the foam material (106) is a rigid or a semi-rigid 10 foam material.
8. (Previously Presented) A thermally insulated container according to claim 1, characterised in that the average diameter of the cells is less than 0.4 mm, preferably less than 0.25 mm.
9. (Previously Presented) A thermally insulated container according to claim 1, characterised in that the coefficient of diffusion of the foam material is less than that of atmospheric air.
10. (Currently Amended) A thermally insulated container according to claim 1, characterised in that the blowing-agent gas comprises ~~cyclopentan~~ cyclopentane.
11. (Previously Presented) A thermally insulated container according to claim 1, characterised in that one of the gases comprises CO₂.
12. (Cancelled)